

**AMENDMENT TO THE SPECIFICATION:**

Table 1 (mixture: wt%)

Friction Material Component	Comparative Examples		Examples		
	1	2	1	2	3
Phenolic resin	10	10	10	10	10
Cashew dust	10	10	10	10	10
Barium sulfate	45	50	45	45	20 [45]
Zirconia	2	2	2	2	2
Graphite	8	8	8	8	8
Copper fibers / Aramid fibers	10/5	10/5	10/5	10/5	10/5
Potassium titanate fibers	5	5	5	5	5
Al <sub>2</sub> O <sub>3</sub> -SiO <sub>2</sub> ceramic fibers	5	-	-	2.5	-
Soluble amorphous fibers	-	-	5	2.5	30

FINNEGAN  
HENDERSON  
FARABOW  
GARRETT &  
DUNNER LLP

1300 I Street, NW  
Washington, DC 20005  
202.408.4000  
Fax 202.408.4400  
www.finnegan.com